

Technical Data Sheet - Sontara® MicroPure 100 small



Property	Value	Test Method
Products Code	2115	
Composition	Polyester 53.5% Woodpulp 46.5%	
Colour	White	
Weight	56 g/m ²	ASTM D3776
Intrinsic absorption capacity	4.0 ml/g	INDA IST 10.2-98
Extrinsic absorption capacity	333 ml/m ²	INDA IST 10.2-98
Intrinsic absorption rate	24.4 ml/g/s	INDA IST 10.2-95
Extrinsic absorption rate	2830 ml/m ² /s	INDA IST 10.2-95
Grab tensile breaking strength	MD 124 N XD 61 N	ASTM D5034
Elongation	MD 27.5% XD 116.5%	ASTM D5034
Extractables in H ₂ O	0.04%	IES RP CC 004.2 sec 6.1
Sheet size	224mm x 224mm	
Sheets per pack	300	
Packs per box	20	
Boxes per pallet	12	

For further information, please contact IPS-Group A/S on:
 Tel.: +45 49 13 28 00
 Mail: INFO@IPS-GROUP.DK