

Technical Data Sheet - Sontara® MicroPure AP small



Property	Value	Test Method
Products Code	2110	
Composition	Polyester 45% Woodpulp 55%	
Colour	White	
Weight	68 g/m ²	ASTM D3776
Intrinsic absorption capacity	4.27 ml/g	INDA IST 10.2-98
Extrinsic absorption capacity	290 ml/m ²	INDA IST 10.2-98
Intrinsic absorption rate	34.0 ml/g/s	INDA IST 10.2-95
Extrinsic absorption rate	2300 ml/m ² /s	INDA IST 10.2-95
Grab tensile breaking strength	MD 156 N XD 89 N	ASTM D5034
Elongation	MD 24% XD 75%	ASTM D5034
Extractables in H ₂ O	0.1%	IES RP CC 004.2 sec 6.1
Sheet size	224mm x 224mm	
Sheets per pack	300	
Packs per box	20	

For further information, please contact IPS-Group A/S on:
 Tel.: +45 49 13 28 00
 Mail: INFO@IPS-GROUP.DK