Sontara. SoftFlush. Softesse. SoftLite.

STYLE 9960

44.5% Woodpulp – 55.5% PET

Flat

TYPICAL MATERIAL PROPERTIES

Test	Orientation	Units	Value	Method
Basis Weight		g/m^2	56	WSP 130.1
Thickness		mm	0.4	WSP 120.6
Absorption Capacity		%	650	WSP 10.1
Extrinsic Absorption Capacity		ml/m^2	350	WSP 10.2
Grab Tensile Strength	MD	N/4in	132	ASTM D5034
	CD	N/4in	67	

These are not specifications and only to be used as indicative properties. All properties are typical values according to our current knowledge at the time of the last update of this publication. They are given for general guidance only – Jacob Holm does not warrant any results and assumes no obligation or liability whatsoever in connection with this information. Please conduct your own tests to ensure consistency for your applications. The publication of these properties does not grant any right or license to any intellectual property of Jacob Holm. MD = machine direction, CD = cross direction – Data last updated March 16, 2017
©2017 Jacob Holm & Sons AG. All rights reserved.

Jacob Holm
MAGIC MEETS FABRIC