

Typical Material Properties Style 9948

TECHNICAL DATA – STYLE 9948

PROPERTY		VALUE	UNIT	TEST METHOD
Basis weight		66	g/m ²	WSP 130.1
Thickness		0.38	mm	WSP 120.6
Composition	Polyester	44	%	
	Woodpulp	56	%	
Absorbency		491	%	WSP 10.1
Extrinsic absorption capacity		327	ml/m ²	WSP 10.2
Grab tensile breaking strength (dry)	MD	315	N	ASTM D5034
	XD	165	N	
Strip tensile breaking strength (dry)	MD	171	N	WSP 110.4
	XD	45	N	

www.sontara.com

All properties are typical values based on roll averages. This is not a specification. Please conduct your own tests to ensure consistency for your application. This information is subject to revision as additional knowledge and experience are gained. Jacob Holm & Sontara® make no guarantee of results and assume no obligation or liability whatsoever in connection with this information. No right or license to any intellectual property of Jacob Holm & Sontara® is intended by the publication of these properties. Nominal values corresponding to our current knowledge, for guidance only. MD=lengthwise, XD=crosswise – last update 25/03/2015.

© 2015 Jacob Holm & Sons AG. All rights reserved. Sontara® is a registered trademark of Jacob Holm & Sons AG.